

**EURO SIL INTONACHINO – *acrylsiloxanic line***

Outdoor wall coating based on siloxanic resins and acrylic dispersions with light-stable pigments and aggregates of marble and silica selected. The progressive interaction between the siloxanic coating and the stone or masonry support helps to strengthen the adhesion over time ensuring exceptional durability. Recommended for the protection of new facilities and the restoration of old buildings.

SPECIFICATIONS

Performance: high water repellency and water vapor permeability.

Composition: siloxanic resins and acrylic dispersions.

Dried product appearance: matt.

Solid content: 72%±2.

Particle size: fine-grained 0,6 mm; medium-grained 0,8 mm;
coarse-grained 1,2 mm.

Abrasion resistance: excellent.

Weathering resistance: excellent.

Strength of adhesion to the substrate: excellent.

Water repellence: excellent.

Water vapor diffusion: excellent.

Ph: 8-8,5.

Application: steel/plastic trowel.

Dilution: ready to use.

Yield: (2 coats) fine-grained 2,2 Kg/sqm; medium-grained 3 Kg/sqm; coarse-grained 4 Kg/sqm, according to the substrate.

UNI EN 15824**CE**

Outdoor wall coating based on
siloxanic resins

Vapor permeability coefficient: V_1

Water absorption: W_3

Adhesion: ≥ 0.3 MPa

Durability: ≥ 0.3 MPa

Thermal conductivity: ($\lambda_{10,dry}$) 0.83 W/m·K (tab.
value; P=50%)

Reaction to fire: Euroclass F

METHOD OF USE

Ensure that the surface is thoroughly dried and aged. If necessary, take measures to reconstruct or consolidate the surface by using specific products. Remove any mold, efflorescence and any old peeling paint by brushing or washing. Remove any deposits of dust, smog or other by brushing. Level any irregularities in the surface and treat holes, cracks, crevices and gaps.

- **New surfaces:** be sure that the plaster is completely seasoned (at least 4-5 weeks). Apply a coat of **Golden Sil Primer** (Caf). When dry, apply two coats of **Euro Sil Intonachino** (Caf) with a steel trowel, spreading the product uniformly; during the step of drying, finish the surface with a trowel sponge with very narrow and regular movements.

- **Already painted surface:** remove the old paint with paint remover **Express** (Caf) and remove any scraps; eliminate the cracks with stucco, if necessary; then proceed as above.



NUOVA CAF S.r.l.

Via L. Einaudi, 6/7_Z.I. – 61032 Fano (PU)_ Italy

Tel. +39 0721 854235 – fax +39 0721 854596

www.nuovacaf.it - info@nuovacaf.it

CLIMATIC CONDITIONS

To avoid compromising the optimal performance of the product, we recommend the application in specific climatic conditions:

- Apply at temperatures between +5 °C and +35 °C;
- Avoid the application on surfaces heated by strong sunlight,
- Avoid application when rain is imminent,
- Avoid application in presence of moisture;
- The painted surface must be kept away from rain and humidity for 48 hours.


USEFUL TIPS:

- Store at room temperature.
- Close the container tightly after each use.
- Protect surfaces not to be painted (windows, tiles, glass etc ...).

Protect from frost.

Packaging: 25 Kg.

Color: white, Allegro color chart, tints on request.

The coloring is possible with the Tinting System 

Washing tools: use water immediately after use.

Specification Item

- > Protect all surfaces not subject to application of paint.
- > Preparation of the surface by manual brushing or washing with high pressure washer machine, depending on the nature and intensity of the dirt. If the surfaces to be treated were covered with organic paints is advisable the total removal of these paintings.
- > Application of outdoor wall coating based on siloxanic resins **Euro Sil Intonachino** (Caf) with a finished thickness of about 2 mm, equivalent to an average consumption of 3 kg/sqm, applied in two coats with a trowel and then sponged, after preparing the substrate with a normalizing primer based on siloxane resins ready to use **Golden Sil Primer** (Caf).
- > All applications must be performed on completely dry surfaces, with the ambient temperature and that of the surfaces to be painted between +5 °C and +35 °C with relative humidity not exceeding 80%. If you ever experience environmental conditions other than those mentioned above, as well as in the presence of wind, dust, smoke, etc ..., the application should not be initiated.

The technical informations contained in this technical sheet are based on our practical experience and laboratory testing and are purely indicative. We offer products and operating systems in perfect correspondence with the highest quality standards, provided that the instructions for use are followed in accordance with the needs and the professional knowledge of utilization. The application of the products takes place outside of our control and therefore is under the sole responsibility of the customer. Our technical department is always at your complete disposal to provide any further information or clarification.