



NUOVA CAF S.r.l.

Via L. Einaudi, 6/7_Z.I. – 61032 Fano (PU)_ Italy

Tel. +39 0721 854235 – fax +39 0721 854596

www.nuovacaf.it - info@nuovacaf.it

AMIANTOBLIND – encapsulation asbestos cement

Elastomeric water-paint based on styrene-acrylic resins suitable for the finishing and protection of structures in cement asbestos, to be used before removal operations as auxiliary encapsulating. The treated surface becomes impermeable to water and walkable. **The product is certified according to UNI 10686 and is suitable for neutralizing of cement-asbestos (reference: D.M. del 20 Agosto 1999-type D).**

SPECIFICATIONS

Composition: styrene-acrylic resins in aqueous emulsion with elastomeric properties.

Nature of charges: titanium dioxide, inert lamellar structure, ventilated quartz, crystalline calcium carbonate.

Strength of adhesion to supports: excellent.

Dilution: ready to use.

Application: spray, brush, roller.

Yield: 4-5 sqm/lit, depending on the degree of deterioration of the surface.

Drying time: about 24 hours, depending on the environmental conditions.

METHOD OF USE

The product is ready for use, apply after proper agitation. To prevent the removal of the fibers during the application it is recommended to spray with low pressure sprayers.

CLIMATIC CONDITIONS

To avoid compromising the optimal performance of the product, we recommend the application in specific climatic conditions:

- Apply at temperatures between +5°C and +35°C;
- Avoid the application on surfaces heated by strong sunlight,
- Avoid application when rain is imminent,
- Avoid application in presence of strong wind,
- Avoid application in presence of moisture;
- The painted surface must be kept away from rain and humidity for 48 hours.

USEFUL TIPS:

- Store at room temperature.
- Close the container tightly after each use.
- Protect surfaces not to be painted (windows, tiles, glass etc ...).

Protect from frost.

Packaging: 15 L.

Color: oxide red.

Washing tools: use water immediately after use.

The technical information contained in this technical sheet are based on our practical experience and laboratory testing and are purely indicative. We offer products and operating systems in perfect correspondence with the highest quality standards, provided that the instructions for use are followed in accordance with the needs and the professional knowledge of utilization. The application of the products takes place outside of our control and therefore is under the sole responsibility of the customer. Our technical department is always at your complete disposal to provide any further information or clarification.



NUOVA CAF S.r.l.

Via L. Einaudi, 6/7_Z.I. – 61032 Fano (PU)_ Italy

Tel. +39 0721 854235 – fax +39 0721 854596

www.nuovacaf.it - info@nuovacaf.it

Specification Item

> Protect all surfaces not subject to application of paint.

> Application by brush, roller or spray of elastomeric water-paint, ready to use and certified according to UNI 10686, to be used before removal operations as auxiliary encapsulating **Amiantoblind** (Caf), respecting a consumption of about 0,200-0,250 lt/sqm, according to the degree of deterioration of the surface.

> All applications must be performed on completely dry surfaces, with the ambient temperature and that of the surfaces to be painted between +5°C and +35°C with relative humidity not exceeding 80%. If you ever experience environmental conditions other than those mentioned above, as well as in the presence of wind, dust, smoke, etc ..., the application should not be initiated.