



**NUOVA CAF S.r.l.**

Via L. Einaudi, 6/7\_Z.I. – 61032 Fano (PU)\_ Italy

Tel. +39 0721 854235 – fax +39 0721 854596

[www.nuovacaf.it](http://www.nuovacaf.it) - [info@nuovacaf.it](mailto:info@nuovacaf.it)

## **AMIANTOFIX – encapsulation asbestos cement**

Solvent-based fixative made with Pliolite Good Year suitable to block the absorption of the slabs in asbestos-cement. After the evaporation of the solvent, the resin contained in the product is able to encapsulate the asbestos fibers that, otherwise, the degradation of cement-asbestos would release into the atmosphere. The tracer phthalo blue highlights where and in what quantity the product is employed. **The product is certified according to UNI 10686 and it is suitable for neutralizing of asbestos concrete products (reference: D.M. del 20 Agosto 1999-tipologia A-B-C).**

### **SPECIFICATIONS**

**Solid concentration:** about 10%.

**Dilution:** ready to use.

**Application:** brush, roller, spray.

**Yield:** it depends on the degree of absorption of asbestos-cement, on the new one you can calculate approximately 0,250 L/sqm, while on asbestos cement old and heavily carbonated you can be up to 0.500 l/sqm.

### **METHOD OF USE**

After performing the cleaning of the sheets and waiting that they are perfectly dry, apply one coat of **Amiantofix** (Caf). After about 24 hours of drying at + 20 °C, apply the finishing.

### **USEFUL TIPS:**

- Store at room temperature.
- Close the container tightly after each use.
- Protect surfaces not to be painted (windows, tiles, glass etc ...).

### **CLIMATIC CONDITIONS**

To avoid compromising the optimal performance of the product, we recommend the application in specific climatic conditions:

- Apply at temperatures between +5 °C and +35 °C;
- Avoid the application on surfaces heated by strong sunlight,
- Avoid application when rain is imminent,
- Avoid application in presence of strong wind,
- Avoid application in presence of moisture;
- The painted surface must be kept away from rain and humidity for 48 hours.

**Protect from frost.**

**Packaging:** 25 L.

**Color:** light blue.

**Washing tools:** use synthetic thinner immediately after use.

The technical information contained in this technical sheet are based on our practical experience and laboratory testing and are purely indicative. We offer products and operating systems in perfect correspondence with the highest quality standards, provided that the instructions for use are followed in accordance with the needs and the professional knowledge of utilization. The application of the products takes place outside of our control and therefore is under the sole responsibility of the customer. Our technical department is always at your complete disposal to provide any further information or clarification.



**NUOVA CAF S.r.l.**

Via L. Einaudi, 6/7\_Z.I. – 61032 Fano (PU)\_ Italy

Tel. +39 0721 854235 – fax +39 0721 854596

[www.nuovacaf.it](http://www.nuovacaf.it) - [info@nuovacaf.it](mailto:info@nuovacaf.it)

## Specification Item

- > Protect all surfaces not subject to application of paint.
- > Preparation of the surface by manual brushing or washing with high pressure washer machine, depending on the nature and intensity of the dirt.
- > Application of one coat of solvent-based fixative certified according to UNI 10686 for the encapsulation of asbestos cement, **Amiantofix** (Caf).
- > All applications must be performed on completely dry surfaces, with the ambient temperature and that of the surfaces to be painted between +5 °C and +35 °C with relative humidity not exceeding 80%. If you ever experience environmental conditions other than those mentioned above, as well as in the presence of wind, dust, smoke, etc ..., the application should not be initiated.