



## ELASTICOL FINITURA – *elastomeric fibrate cycle*

Elastomeric-acrylic emulsion paint formulated with dispersions of acrylic resins photosensitive equipped with exceptional elasticity and at the same time a good surface hardness, inert carefully selected, and it has a crystalline structure such as to protect the binder by the action of UV rays. Fully compatible with Elasticol Fondo, it is the ideal complement to complete optimally the elastomeric cycle. It adapts to the movement of the surface without cracking and it protects the whole system from the degrading effects of atmospheric agents.

### SPECIFICATIONS

**Performance:** permanent elasticity also able to endure considerable stresses; excellent adhesion; high water repellency and resistance to soiling; it offers a high degree of protection against aggressive environmental conditions.

**Composition:** styrene-acrylic resins, synthetic fibers, selected aggregates with lamellar structure.

**Appearance of dried product:** smooth, satin-finished.

**Solid content:** 58±2.

**Particle size:** 60-70 µ.

**Viscosity at 20°C:** 25.000 cps ± 2.000 cps (A6 20').

**Abrasion resistance:** excellent.

**Average thickness of the film:** 70-80 µ.

**Weathering resistance:** excellent.

**Strength of adhesion to the substrate:** excellent.

**Ph:** 8,5-9.

**Application:** brush, roller.

**Dilution:** ready to use, max. 5-10% water.

**Yield:** 5-6 sq.m/L, depending on the absorbency of the support.

**Drying time:** 16-24 hours, in normal condition of temperature and humidity.

### METHOD OF USE

Ensure that the surface is thoroughly dried and aged. If necessary, take measures to reconstruct or consolidate the surface by using specific products. Remove any mold, efflorescence and any old peeling paint by brushing or washing. Remove any deposits of dust, smog or other by brushing. Level any irregularities in the surface and treat holes, cracks, crevices and gaps.

- *New surface:* If in the surface to be treated there are cracks, due to settling or other reasons, it must open them, soak several times the edge with **Primer Consolidante** and once dry close the cracks with a stucco formed by **Elasticol Fondo** mixed with fine-grained sand. Otherwise apply **Primer Consolidante** on the entire surface. Wait at least 12 hours and proceed applying **Elasticol Fondo**. Then apply two coats of **Elasticol Finitura** in the desired tone, waiting at least 24 between both.

- *Already painted surface:* remove the old paint with the paint remover Express and remove all debris; fill if necessary, apply of nitro-based primer Fix Nitro alla Pliolite, then apply Elasticol Fondo and Elasticol Finitura, as above.



CLIMATE CONDITIONS

**NUOVA CAF S.r.l.**

Via L. Einaudi, 6/7\_Z.I. – 61032 Fano (PU)\_ Italy

Tel. +39 0721 854235 – fax +39 0721 854596

[www.nuovacaf.it](http://www.nuovacaf.it) - [info@nuovacaf.it](mailto:info@nuovacaf.it)

To avoid compromising the optimal appearance and performance of the product we recommended that it be applied only in specific climate conditions:

- Apply to temperatures between +5 °C and +35 °C;
- Avoid the application on surfaces heated by strong sunlight,
- Avoid application when rain is imminent,
- Avoid application in case of humidity;
- Surface must be protected from rain and damp for approximately 48 hours.

#### USEFUL TIPS

- Store at room temperature.
- Close the container tightly after each use.
- Protect surfaces not to be painted (windows, tiles, glass etc ...).

**Protect from frost.**

**Packaging:** 14 L.

**Color:** white, Allegro color chart.

**Washing tools:** use water immediately after use.

## Specification Item

- > Protect all surfaces not subject to application of paint.
- > Preparation of the surface by manual brushing or washing with high pressure washer machine, depending on the nature and intensity of the dirt.
- > Application by roller or brush of two coats of **Elasticol Finitura** (Caf) spaced from each other by at least 24 hours, respecting an average consumption of 0.250 L/sqm, after the preparation surface with a solvent -based fixative **Primer Consolidante** (Caf) and a layer of **Elasticol Fondo** (Caf), respecting an average consumption of 0.700 L/sqm for the complete performance development.
- > All applications must be performed on completely dry surfaces, with the ambient temperature and that of the surfaces to be painted between +5 °C and +35 °C with relative humidity not exceeding 80%. If you ever experience environmental conditions other than those mentioned above, as well as in the presence of wind, dust, smoke, etc ..., the application should not be initiated.

The technical information contained in this technical sheet are based on our practical experience and laboratory testing and are purely indicative. We offer products and operating systems in perfect correspondence with the highest quality standards, provided that the instructions for use are followed in accordance with the needs and the professional knowledge of utilization. The application of the products takes place outside of our control and therefore is under the sole responsibility of the customer. Our technical department is always at your complete disposal to provide any further information or clarification.