



PINTOIL TOP SATINATO – *solvent based enamel*

Synthetic, top quality enamel for outdoor use with satin finishing. With excellent resistance to weathering, industrial corrosion and marine action. It has high resistance to yellowing, excellent elasticity and exceptional coverage. It can be used on any structure in iron, wood, PVC, and on all wall surfaces; it is particularly suitable for structures in marine environments. Its ease of application combined with excellent product quality ensure durability of the aesthetic features of the surface painted.

SPECIFICATIONS

Composition: medium oil alkyd non-yellowing resins.

Nature of the pigments: inorganic and organic highly resistant to weathering.

Solid content: 65%±2.

Recommended film thickness per coat: 25-35 µ.

Dried product appearance: satin.

Viscosity at 20 ° C: 5-20".

Application: brush, roller, spray.

Dilution: 5% approx. with white spirit.

Yield: 6-7 sqm/ltr, 2 coats.

Drying time: to touch 5-6 hours, hardened in depth 24 hours.

Recoat: 18-24 hours under normal conditions of temperature and humidity.

METHOD OF USE

Ensure that the surface is thoroughly dried and aged. If necessary, take measures to reconstruct or consolidate the surface by using specific products. Remove any deposits of dust, smog or other by brushing. Level any irregularities in the surface and treat holes, cracks, crevices and gaps.

- *Never painted wood/walls:* sanding and putty if necessary, then apply a coat of solvent-based undercoat **Pintopac** (Caf). Make sure the product is completely dry before applying **Pintoil Top Satinato** (Caf).

- *Never painted iron:* brush and sand the surface, removing all traces of rust; clean and degrease with nitro thinner. Treat the surface with a coat of **Minio** (Caf) or **Antiruggine** (Caf); wait 16-24 hours and apply two coats of **Pintoil Top Satinato** (Caf).

- *Already painted surface:* remove the parts of paint not well anchored with the paint stripper **Express** (Caf); sand and putty if necessary; then proceed as above.

CLIMATIC CONDITIONS

To avoid compromising the optimal performance of the product, we recommend the application in specific climatic conditions:

- Apply at temperatures between +5 °C and +35 °C;
- Avoid the application on surfaces heated by strong sunlight,
- Avoid application when rain is imminent,
- Avoid application in presence of moisture;
- The painted surface must be kept away from rain and humidity for 48 hours.

The technical information contained in this technical sheet are based on our practical experience and laboratory testing and are purely indicative. We offer products and operating systems in perfect correspondence with the highest quality standards, provided that the instructions for use are followed in accordance with the needs and the professional knowledge of utilization. The application of the products takes place outside of our control and therefore is under the sole responsibility of the customer. Our technical department is always at your complete disposal to provide any further information or clarification.



NUOVA CAF S.r.l.

Via L. Einaudi, 6/7_Z.I. – 61032 Fano (PU)_ Italy

Tel. +39 0721 854235 – fax +39 0721 854596

www.nuovacaf.it - info@nuovacaf.it

USEFUL TIPS:

- Store at room temperature.
- Close the container tightly after each use.
- Protect surfaces not to be painted (windows, tiles, glass etc ...).

Protect from frost.

Packaging: 0,375 - 0,750 – 2,5 L.

Color: RAL colors.

Washing tools: use white spirit immediately after use.

Specification Item

- > Protect all surfaces not subject to application of paint.
- > Preparation of the substrate by manual brushing or washing with high pressure washer machine, depending on the nature and intensity of the dirt.
- > Application of one coat of solvent-based anticorrosive undercoat **Antiruggine** (Caf) by roller, brush or spray. Once dried, application of two coats of synthetic solvent-based top quality enamel with satin finishing **Pintoil Top Satinato** (Caf), waiting 18-24 hours between coats, making a dry thickness of 25-35 μ per coat.
- > All applications must be performed on completely dry surfaces, with the ambient temperature and that of the surfaces to be painted between +5 °C and +35 °C with relative humidity not exceeding 80%. If you ever experience environmental conditions other than those mentioned above, as well as in the presence of wind, dust, smoke, etc ..., the application should not be initiated.

The technical information contained in this technical sheet are based on our practical experience and laboratory testing and are purely indicative. We offer products and operating systems in perfect correspondence with the highest quality standards, provided that the instructions for use are followed in accordance with the needs and the professional knowledge of utilization. The application of the products takes place outside of our control and therefore is under the sole responsibility of the customer. Our technical department is always at your complete disposal to provide any further information or clarification.