



NUOVA CAF S.r.l.

Via L. Einaudi, 6/7_Z.I. – 61032 Fano (PU)_ Italy

Tel. +39 0721 854235 – fax +39 0721 854596

www.nuovacaf.it - info@nuovacaf.it

PLIOFIX – solvent-based primers

Pigmented solvent-based undercoat for external use, formed by Goodyear Pliolite resins and characterized by a good penetration and consolidation power. It applies to any type of plaster also very absorbent or crumbling.

SPECIFICATIONS

Composition: styrene-acrylate copolymer.

Solvents: aromatic hydrocarbons.

Dry resin on total dry: 18%.

Application: brush, spray.

Dilution: 30-40% with white spirit.

Yield: 6-7 sqm/L, with one coat according to the absorption of the substrate.

Drying time: dry in depth in 24 hours, depending on the environmental conditions.

METHOD OF USE

Ensure that the surface is thoroughly dried and aged. If necessary, take measures to reconstruct or consolidate the surface by using specific products. Remove any mold, efflorescence and any old peeling paint not well anchored by brushing or washing. Remove any deposits of dust, smog or other by brushing. Level any irregularities in the surface and treat holes, cracks, crevices and gaps.

Scrape and brush the surface, removing any debris, then apply a layer of Pliofix. Wait at least 24 hours before applying the finishing product.

CLIMATE CONDITIONS

To avoid compromising the optimal appearance and performance of the product we recommended that it be applied only in specific climate conditions:

- Apply to temperatures between +5 °C and +35 °C;
- Avoid the application on surfaces heated by strong sunlight,
- Avoid application when rain is imminent,
- Avoid application in case of humidity;
- Surface must be protected from rain and damp for approximately 48 hours.

USEFUL TIPS

- Store at room temperature.
- Close the container tightly after each use.
- Protect surfaces not to be painted (windows, tiles, glass etc ...).

Protect from frost.

Packaging: 16 L.

Color: Allegro color chart.

Washing tools: use nitro thinner immediately after use.

The technical information contained in this technical sheet are based on our practical experience and laboratory testing and are purely indicative. We offer products and operating systems in perfect correspondence with the highest quality standards, provided that the instructions for use are followed in accordance with the needs and the professional knowledge of utilization. The application of the products takes place outside of our control and therefore is under the sole responsibility of the customer. Our technical department is always at your complete disposal to provide any further information or clarification.



NUOVA CAF S.r.l.

Via L. Einaudi, 6/7_Z.I. – 61032 Fano (PU)_ Italy

Tel. +39 0721 854235 – fax +39 0721 854596

www.nuovacaf.it - info@nuovacaf.it

Specification Item

- > Protect all surfaces not subject to application of paint.
- > Preparation of the surface by manual brushing or washing with high pressure washer machine, depending on the nature and intensity of the dirt.
- > Application of a coat of pigmented solvent-based primer for external use formed by Goodyear Pliolite resins **Pliofix** (CAF), diluted to 30-40% with white spirit, respecting a consumption of about 0.15 L/sq.m. according to the type of surface.
- > All applications must be performed on completely dry surfaces, with the ambient temperature and that of the surfaces to be painted between +5 °C and +35 °C with relative humidity not exceeding 80%. If you ever experience environmental conditions other than those mentioned above, as well as in the presence of wind, dust, smoke, etc ..., the application should not be initiated.